CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: T- 4358

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-05-26-02** **Date: 31-05-17**

Customer : Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.

Address : Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Providing and Construction of CC road near Eagle Bakery back side Dhaneshwari Nagara. T.Dasarahalli in Ward No. 15 Dasarahalli Sub Division

Agency : Sri. N. Thippeswamy, #09, 1st Cross, Saraswathi Puram, Bangalore gate, Chithraduraga.

Customer's Reference : EE/DD/WO/24/17-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-05-17

Sample ID No : 2017-05-26-02/01

Customer ID : M20 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/05/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	24/05/2017	31/05/2017	151.00 X 149.29 X 151.09	22543	8.196	394.5	17.5	17.6
2	M20 Concrete	M20	24/05/2017	31/05/2017	150.29 X 150.83 X 150.22	22668	8.172	410.3	18.1	
3	M20 Concrete	M20	24/05/2017	31/05/2017	150.27 X 150.28 X 150.27	22583	8.175	390.7	17.3	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harsitha

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: T- 4358

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2017-05-26-02** **Date: 21-06-17**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Providing and Construction of CC road near Eagle Bakery back side Dhaneshwari Nagara. T.Dasarahalli in Ward No. 15 Dasarahalli Sub Division
Agency	:	Sri. N. Thippeswamy, #09, 1st Cross, Saraswathi Puram, Bangalore gate, Chithraduraga.
Customer's Reference	:	EE/DD/WO/24/17-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	26-05-17
Sample ID No	:	2017-05-26-02/02
Customer ID	:	M20 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	21/06/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M20 Concrete	M20	24/05/2017	21/06/2017	150.22 X 149.98 X 151.53	22530	8.076	534.0	23.7	23.8
2	M20 Concrete	M20	24/05/2017	21/06/2017	150.76 X 150.28 X 151.07	22656	8.169	546.0	24.1	
3	M20 Concrete	M20	24/05/2017	21/06/2017	151.38 X 151.91 X 151.88	22996	8.197	540.4	23.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harsitha

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF FINE AGGREGATE

Date: 20-05-17

Lab ID	:	**CP-2017-05-16-06**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Providing and Construction of CC road near Eagle Bakery back side Dhaneshwari Nagara. T.Dasarahalli in Ward No. 15 Dasarahalli Sub Division
Agency	:	Sri. N. Thippeswamy, #09, 1st Cross, Saraswathi Puram, Bangalore gate, Chithraduraga.
Customer's Reference	:	EE/DD/WO/24/17-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	16-05-17
Sample ID No	:	2017-05-16-06/03
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	16-05-17
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0	100	100	100	100	100
2	4.75 mm	28	28	2.8	97.2	90-100	90-100	90-100	95-100
3	2.36 mm	187	215	21.5	78.5	60-95	75-100	85-100	95-100
4	1.18 mm	154	369	36.9	63.1	30-70	55-90	75-100	90-100
5	600 micron	172	541	54.1	45.9	15-34	35-59	60-79	80-100
6	300 micron	225	766	76.6	23.4	5-20	8-30	12-40	15-50
7	150 micron	195	961	96.1	3.9	0-10	0-10	0-10	0-15
8	Pan	39	1000	100	0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2017-05-16-06** **Date: 20-05-17**

Sample ID No : 2017-05-16-06/03

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.85	_
2	Specific Gravity	2.56	_
3	Material finer than 75 micron(%)	3.5	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

FOR CIVIL Pro.
CIVIL Pro Sig..... Date..... BANGALORE
R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಆಯುಕ್ತರ ಕಾರ್ಯಾಲಯ ಆಡಳಿತಾಧಿಕಾರಿ
ಬಿ ಬಾಸವನಗುಡಿ ಉಪ-ವಿಭಾಗ
ಬೆಂಗಳೂರು ಪಟ್ಟಣ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: T- 4358

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2017-05-16-06** **Date: 20-05-2017**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Providing and Construction of CC road near Eagle Bakery back side Dhaneshwari Nagara. T.Dasarahalli in Ward No. 15 Dasarahalli Sub Division
Agency	:	Sri. N. Thippeswamy, #09, 1st Cross, Saraswathi Puram, Bangalore gate, Chithraduraga.
Customer's Reference	:	EE/DD/WO/24/17-18
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	16-05-17
Sample ID No	:	2017-05-16-06/02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	16-05-17

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	876	876	5.8	94.2	90-100
3	20 mm	8219	9095	60.6	39.4	30-70
4	10 mm	2871	11966	79.8	20.2	10-35
5	4.75 mm	2705	14671	97.8	2.2	0-5
6	Pan	329	15000	100.0	0	---

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

CIVIL PRO BANGALORE Sig..... Date.....

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2017-05-16-06** **Date: 20-05-2017**

Sample ID No : 2017-05-16-06/02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	10.6	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.2	
3	Specific Gravity	2.62	_
4	Bulk Density(Loose) (Kg/l)	1.49	_
5	Bulk Density(Compacted) (Kg/l)	1.55	_
6	Water Absorption(%)	0.23	_

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

TEST REPORT ON COARSE AGGREGATES

Date: 20-05-2017

Lab ID	:	**CP-2017-05-16-06**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Providing and Construction of CC road near Eagle Bakery back side Dhaneshwari Nagara. T.Dasarahalli in Ward No. 15 Dasarahalli Sub Division
Agency	:	Sri. N. Thippeswamy, #09, 1st Cross, Saraswathi Puram, Bangalore gate, Chithraduraga.
Customer Reference	:	EE/DD/WO/24/17-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	16-05-17
Sample ID No	:	2017-05-16-06/02(b)
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	16-05-17

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	218	218	4.4	95.6	90-100
3	10 mm	2891	3109	62.2	37.8	25-55
4	4.75 mm	1776	4885	97.7	2.3	0-10
5	Pan	115	5000	100	0	–

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2017-05-16-06** **Date: 20-05-2017**

Sample ID No : 2017-05-16-06/02(b)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.1	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	10.8	
3	Specific Gravity	2.61	–
4	Bulk Density(Loose) (Kg/l)	1.51	–
5	Bulk Density(Compacted) (Kg/l)	1.58	–
6	Water Absorption(%)	0.23	–
7	Aggregate crushing Value(%)	24.1	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	21.5	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

FOR CIVIL Pro.
CIVIL PRO BANGALORE Sig..... Date.....
R KARTHIK RECHAN
Authorized Signature
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯ ಪಾಲಕ ಅಭಿಯಂತರರು
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2017-05-16-06** **Date: 19-05-2017**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Providing and Construction of CC road near Eagle Bakery back side Dhaneshwari Nagara. T.Dasarahalli in Ward No. 15 Dasarahalli Sub Division.
Agency	:	Sri. N. Thippeswamy, #09, 1st Cross, Saraswathi Puram, Bangalore gate, Chithraduraga.
Customer's Reference	:	EE/DD/WO/24/17-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	16-05-17
Sample ID No	:	2017-05-16-06/01
Sample Type	:	Zuari 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	17-05-17

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.92	_
2	Finess by Air permeablity method (m^2/kg, Min)	281.1	225m^2/kg, Min
3	Density (gm/cc)	3.17	_
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	245 minutes	Not less than 30 minutes
6	Final Setting time	235 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.0mm	Not more than 10 mm

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯ ಪಾಲಕ ಅಭಿಯಂತರರು
ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

****End of Report****

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2017-05-16-06** **Date: 14-06-2017**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Providing and Construction of CC road near Eagle Bakery back side Dhaneshwari Nagara. T.Dasarahalli in Ward No. 15 Dasarahalli Sub
Agency	:	Sri. N. Thippeswamy, #09, 1st Cross, Saraswathi Puram, Bangalore gate, Chithraduraga.
Customer's Reference	:	EE/DD/WO/24/17-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	16-05-17
Sample ID No	:	2017-05-16-06/01
Sample Type	:	Zuari 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	17-05-17

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	29.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	38.5N/mm^2	Not less than 37 N/mm^2
3	28 Days	54.0N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Prepared by
Harshitha

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

****End of Report****

Name Of Work: Providing and Construction of C.C road near Eagle Bakery back side Dhaneshwari Nagara, T. Dasarahalli in Ward No. 15 Dasarahalli Sub Division

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು